

PRODUCT DATA SHEET

CONCRETE AGGREGATE 20 x 10mm

Product Code: ABF259

PRODUCT DESCRIPTION

ASMS ABF259 is a 20 x 10 mm concrete aggregate conforming to AS2758.1 - 20 mm graded aggregate.

APPLICATIONS

ASMS ABF259 is manufactured as an aggregate for use in concrete.

COMPOSITION AND MATERIALS

ABF259 is produced by crushing and screening blast furnace slag to a single size 10mm aggregate consisting of angular to roughly cubical shaped particles with a characteristically vesicular structure and rough surface texture. Aggregates are aged and watered to achieve the target SSD.

Blast furnace slag is the non-metallic product consisting essentially of silicates and aluminosilicates of calcium and other bases developed in a molten condition simultaneously with iron in a blast furnace.

Air-cooled blast furnace slag is a predominantly crystalline, solid rock-like material.

ADVANTAGES

- Consistent chemistry.
- Excellent load bearing capacity.
- Non-plastic.
- Resistant to heat and fire.
- Vesicular surface improves mechanical interlock.
- Economic alternative to natural aggregates.
- Effective utilisation of an industrial by-product conserving natural resources.

TYPICAL GRADING

SIEVE	% PASSING
26.5 mm	100
19.0 mm	97
13.2 mm	60
9.5 mm	28
4.75 mm	10
2.36 mm	7

TYPICAL PHYSICAL PROPERTIES

PROPERTY	UNIT	TYPICAL
Bulk Density (Loose)	t/m ³	1.2-1.4
Bulk Density (Compacted)	t/m ³	1.3-1.5
Particle Density (Apparent)	t/m ³	2.70-2.90
Particle Density (Dry)	t/m ³	2.45-2.65
Particle Density (SSD)	t/m ³	2.55-2.75
Wet Strength	kN	70-90
Dry Strength	kN	80-100
Water Absorption	%	2.5-5.5
Chlorides	%	<0.05
Sulphates as SO ₃	%	<0.2
Alkali Reactivity	-	Innocuous
Sugar	-	Free
Iron Unsoundness	-	Free

OXIDE ANALYSIS

CONSTITUENT	SYMBOL	%
Iron Oxide	FeO	0.5
Calcium Oxide	CaO	42
Silicon Dioxide	SiO ₂	35
Aluminium Oxide	Al ₂ O ₃	14
Magnesium Oxide	MgO	6
Sulphur	S	0.5
Sodium Oxide	Na ₂ O	0.3

TECHNICAL AND CUSTOMER ENQUIRIES

Telephone: (02) 4255 1100

Email: enquiries@asms.com.au

ASMS DISCLAIMER

The information contained in this Product Data Sheet is accurate for general consideration, however, no warranty is expressed or implied regarding the accuracy of this data on specific applications. Information is furnished upon the condition that the user shall obtain specific advice and/or carry out tests to determine suitability for a particular purpose and for specific site and application conditions. Sales specifications, although current at the time of publication, are subject to change due to process improvements. For the latest product specifications or usage updates contact ASMS. PDS-GBF006: Rev. 5: 05.03.24 1/1